

classification report

Title:

CLASSIFICATION OF
REACTION TO FIRE
PERFORMANCE
IN ACCORDANCE WITH
EN 13501-1: 2007

Notified Body No:

0833

Product Name:

Corian® FR Solid Surface
Sheeting

Report No:

185005

Issue No:

1

Prepared for:

DuPont De Nemours
(Belgium) NV
Corian Department
Antoon Spinostraat 6
B-2800 Mechelen
Belgium

Date:

14th July 2009

1. Introduction

This classification report defines the classification assigned to Corian® FR Solid Surface Sheeting in accordance with the procedures given in EN 13501-1:2007

2. Details of classified product

2.1 General

The product, Corian® FR Solid Surface Sheeting, is defined as being suitable for wall or ceiling applications. excluding flooring and linear pipe thermal insulation.

2.2 Product description

The product, 'Corian® FR Solid Surface Sheeting', is fully described below and in the test reports provided in support of classification listed in Clause 3.1.

General description		Solid Surface Sheeting
Product reference of wall covering		CORIAN® FR SOLID SURFACE SHEETING
Name of manufacturer		E. I. du Pont de Nemours and Company
Overall thickness		12.3 ± 0.7mm mm (Stated by sponsor) 12.5mm (Determined by Exova warringtonfire)
Total density		1695kg/m ³ to 1770kg/m ³ . (Stated by sponsor) 1744g/ m ³ (Determined by Bodycote warringtonfire)
Colour		Any
Composition of Product		The product comprises a mixture of polymethylmethacrylate resin, pigments and mineral fillers.
Adhesive	Product reference	"Corian®" silicone sealant
	Generic type	Silicone
	Name of manufacturer	E. I. du Pont de Nemours and Company
Substrate	Generic type	Gypsum Plasterboard
	Supplier	Knauf
	Thickness	9.5mm
Description of Manufacturing Process		Note 1

Note 1: The sponsor of the test has provided this information which is held on confidential file at Exova Warringtonfire

3. Test reports/extended application reports & test results in support of classification

3.1 Test reports/extended application reports

Name of Laboratory	Name of sponsor	Test reports/extended application report Nos.	Test method / extended application rules & date
Warrington Fire Research Centre	DuPont Corian	WARRES 128275, 128276, 128279, 128280	EN 13823
Warrington Fire Research Centre	DuPont Corian	WARRES 128425, 128423	EN ISO 11925-2

3.2 Test results

Test Method	Parameter	Number of Tests	Results	
			Continuous Parameter - mean (m)	Compliance Parameters
EN ISO 11925-2 30s exposure surface 30s exposure edge flaming droplets/particles	$F_s \leq 150\text{mm}$	6, 6	0, 0	Y
	$F_s \leq 150\text{mm}$	6, 6	15, 20	Y
	Ignition of filter paper		(-), (-)	Y
EN 13823	$\text{FIGRA}_{0.2\text{MJ}} \leq 120 \text{ W/s}$	3, 3, 3, 3	29.48, 30.21, 41.76, 38.98	Y
	$\text{THR}_{600\text{s}} \leq 7.5 \text{ MJ}$		4.56, 4.86, 6.58, 6.07	Y
	LFS < edge		No	Y
	$\text{SMOGRA} \leq 30 \text{ m}^2/\text{s}^2$		0.33, 0,0, 3.13	Y
	$\text{TSP}_{600\text{s}} \leq 50 \text{ m}^2$		10.65, 8.52, 10.67, 6.76	Y

4. Classification and field of application

4.1 Reference of classification

This classification has been carried out in accordance with clause 8 of EN 13501-1:2007

4.2 Classification

The product, Corian® FR Solid Surface Sheetting, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction products is:

Fire Behaviour		Smoke Production			Flaming Droplets	
B		s	1	,	d	0

ie **B – s1 , d0**

Reaction to fire classification: B – s1 , d0

4.3 Field of application

This classification is valid for the following end use applications:

- i) Construction applications used over any substrate with a density equal to or greater than 1800Kg/m³, having a minimum thickness of 6mm and a fire performance of A2 or better.
- ii) Product installed utilising Corian® silicone sealant only.

This classification is also valid for the following product parameters:

Product thickness	Between 12.3mm (\pm 0.7mm)
Product density	Between 1695kg/m ³ and 1770kg/m ³
Product composition	No variation allowed
Product colour/pattern	Any colour variation allowed
Product construction	No variation allowed


5. Limitations

This document does not represent type approval or certification of the product

SIGNED



APPROVED



.....
Simon Ince
Certification Engineer
Technical Department

.....
Janet Murrell
Technical Manager
Technical Department
on behalf of **Bodycote Warringtonfire**

This copy has been produced from a .pdf format electronic file that has been provided by Bodycote **warringtonfire** to the sponsor of the report and must only be reproduced in full. Extracts or abridgements of reports must not be published without permission of Bodycote **warringtonfire**. The original signed paper version of this report is the sole authentic version. Only original paper versions of this report bear authentic signatures of the responsible Bodycote **warringtonfire** staff.

ANNEX 1

The following list of products are those in the DuPont De Nemours (Belgium) NV range which comply with the description of product for which this classification applies:

CORIAN® GENESIS FR
CORIAN® SIERRA FR
CORIAN® VENARO FR
CORIAN® JEWEL FR



Bodycote warringtonfire • Head Office • Holmesfield Road • Warrington • Cheshire • WA1 2DS • United Kingdom
Tel: +44 (0) 1925 655 116 • Fax: +44 (0) 1925 655 419 • Email: Info@warringtonfire.net • Website: www.warringtonfire.net

